Iridiscent Colour Blends



Suitability area product & Composition guide

Wall	Floor	Wet areas	Pools	Materials	
Int / Ext No		Yes	Yes	Glass	

Technical Characteristics

Test UNE-EN-ISO 10545-3	Test UNE-EN-ISO 101-92=101	Test UNE-EN-ISO 10545-9	Test UNE-EN-ISO 10545-12	Test UNE-EN-ISO 10545-13:1998 Resistance to chemical attack.			
Water Absorption.	Surface hardness. Mohs.	Resistance to thermal shocks.	Frost Resistance.	Domestic Products.	Pool water additives.	Low acid and alkalins.	High acid and alkalins.
None	4	Resistant	Resistant	GA	GA	GLA	GHA
Test UNE-EN-ISO 10545-14	Test UNE-EN-ISO 10545-11=1997	DIN 51094	DCOF		DIN 51130:2004 SLIP	DIN 51097 SLIP	Test UNE-ENV 12633:2003 (CTE)
Resistance to staining.	Cracking.	Colour Stability on exposure to light and UV rays.	Wet Dynamic Coefficient of Friction ANSI A 137.1 Standard.		Resistance wearing shoes.	Resistance in bare feet.	Anti skid coeffi- cient, suitable for outdoor use and swimming pools.
Class 5	Resistant	Resistant					

Packing

Sheet Hoja	4,7 mm - 0.185" Thickness	311x467 mm - 12.24"x18.38"	1,3 kg - 2.86 lb	
Box Caja	14 Sheets	2,03 m² - 21.85 sqft	18,7 kg - 41.22 lb	
Pallet Palet	Pallet Palet 60 Boxes		1131,9 kg - 2495.41 lb	
Euro Pallet Euro Palet 50 Boxes		101,5 m² - 1092.53 sqft	957,1 kg - 2110.04 lb	



Made in Spain

98% Recycled Glass



Ø

Green & Sustainable Products

All ONIX 98% recycled glass mosaics series are made of molten glass. Molten glass characteristics may include irregular edges and small variations in size. These characteristics are inherent to the product and to the standard production. The small size and shape variations can affect the grout joint appearance and enhance the natural aspect of these products.

